

Stripping & Polish Application

1. Dust mop the entire floor area
2. Use Actichem's AP400 Instastrip or AP402 Safe Strip @ 1:4 in a mop and bucket.
3. Liberally apply solution to floor area with a mop. Allow 5-10 minutes dwell time. Ensure that the solution does not dry on the floor during this time.
4. Scrub with auto-scrubber or low speed buffer and black pads. Detail edges with edging tool.
5. Apply clean water with auto-scrubber and pick up dirty solution with auto-scrubber or wet/dry vacuum. Rinse floor a second time using clean water and a clean mop to ensure that no residue is left behind.
6. Apply one even coat of AP420 Instaseal. Coverage is approximately 40m² per litre.
7. Once dry, apply three even coats of AP422 Instagloss or AP423 Instashine. Coverage is approximately 50m² per litre.
8. Allow approximately 45 minutes between coats.
9. An extra coat may be necessary in high traffic areas.

Routine Maintenance

The frequency of routine maintenance will depend on the amount of foot traffic, the desired appearance and the environment in which the floor is located.

1. Sweep regularly and spot clean to remove general spillages.
 2. Scrub floor with auto-scrubber or mop and bucket. Use AP662 Proneutro for general cleaning (1:200 in auto-scrubber or 1:100 in mop and bucket).
 3. After cleaning the floor can be buffed using a buffing machine and AP412 Instabuff Super.
 4. Dust mop floor.
- Entrance matting will help to preserve the life of the polish.

Cutting back & Re-coating (approximately every 3 months)

1. Dust mop entire floor area
2. Scrub floor with auto-scrubber and a red floor maintenance pad. Use AP662 Proneutro (1:200 in auto-scrubber).
3. Trail clean rinse mop behind auto-scrubber.
4. Buff floor with red buffing pad, followed by dust catch mop.
5. Apply two coats of AP422 Instagloss or AP423 Instashine.
6. Clean polish applicator with water.